

## ASTM Property

<b>Grade</b>	VL730
<b>Product</b>	EVA

### General Information

**Key Features**

- VL730 resin is produced by ExxonMobil Chemical's autoclave process technology.
- VL730 resin, with 18% VA content, is an excellent raw material in the application of Extrusion Coating.

**Applications** - Extrusion Coating : BOPP / PET Film, Paper, Tarpaulin, etc.

Item	Measuring Method	Unit	Value
<b>Physical</b>			
Melt Flow Index	ASTM D1238	g/10min	15.0
Vinyl acetate	LDP Method	wt.%	18.0
<b>Mechanical</b>			
Tensile Stress (Break)	ASTM D638	kgf/cm <sup>2</sup>	140
Elongation (Break)	ASTM D638	%	≥700
<b>Thermal</b>			
Melting Point	LDP Method	°C	84
VICAT Softening Temperature	ASTM D1525	°C	55

1. Physical Properties : these are not to be construed as specifications
2. ISO 9001, 14001

\* The last update date : 2026/06/01