

DATASHEET

ASTM Property



Grade	U8835H
Product	LLDPE

General Information

Key Features

U8835H is a linear low density polyethylene extrusion coating grade especially designed for the tarpaulin extrusion coating application providing good heat sealing, good draw down ability.

Applications

Tarpaulin Extrusion Coating

Item	Measuring Method	Unit	Value
Physical			
Melt Flow Index	ASTM D1238	g/10min	16
Density	ASTM D1505	g/cm ³	0.923
VICAT Softening Temperature	ASTM D1525	°C	94
Neck-in 50m/min, 315 °C	LDP Method	cm	5.9
150m/min, 315°C			4.8
Minimum coating weight	LDP Method	g/m ²	6

1. Physical Properties : these are not to be construed as specifications
2. ISO 9001, 14001

* The last update date : 2026/06/01